

Exac PFA

Perfluoroalkoxy
Saint Gobain - Norton

Message:

Exac PFA is a Perfluoroalkoxy (PFA) product. It is available in North America. Applications of Exac PFA include engineering/industrial parts, electrical/electronic applications, aerospace, automotive and medical/healthcare.

Characteristics include:

Flame Rated

Chemical Resistant

Good Weather Resistance

Heat Resistant

General Information			
Features	Good Chemical Resistance		
	Good Thermal Stability		
	Good Weather Resistance		
	Low Friction		
	Machinable		
	Self Lubricating		
Uses	Aerospace Applications		
	Automotive Applications		
	Bearings		
	Bushings		
	Connectors		
	Electrical Parts		
	Insulation		
	Medical Devices		
	Pump Parts		
	Seals		
Agency Ratings	ASTM D 3307		
Forms	Rod		
	Tubing		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.14	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.030	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method

Tensile Modulus	276	MPa	ASTM D638
Tensile Strength (Yield)	28.6	MPa	ASTM D638
Tensile Elongation (Yield)	330	%	ASTM D638
Flexural Modulus	689	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (24°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	73.3	°C	
1.8 MPa, Unannealed	47.8	°C	
Continuous Use Temperature	260	°C	ASTM D794
Brittleness Temperature	-196	°C	ASTM D746
Melting Temperature	302 to 310	°C	
CLTE - Flow	1.2E-4	cm/cm/°C	ASTM D696
Thermal Conductivity	0.26	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	ASTM D257
Volume Resistivity	1.0E+18	ohms·cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	2.10		
1 MHz	2.10		
Dissipation Factor			ASTM D150
60 Hz	2.5E-4		
1 MHz	3.0E-4		
Arc Resistance	180	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT