

UTTAP QU BM513 GF

Polyamide
Ovation Polymers Inc.

Message:
Glass reinforced (13 %) High Temperature Polyamide - Blow Molding grade with excellent chemical resistance, improved flow and high HDT.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Features	Good Chemical Resistance		
	Good Flow		
Forms	Pellets		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (280°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow : 3.17 mm	0.0 to 0.50	%	
Across Flow : 3.17 mm	0.90 to 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3500	MPa	ASTM D638
Tensile Strength ² (Yield)	100	MPa	ASTM D638
Tensile Elongation ³ (Break)	4.0	%	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	4300	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	135	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	230	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

