

ResMart Plus HDPE 5502

High Density Polyethylene

ResMart

Message:

HDPE copolymer for blow molding and extrusion

General Information			
Uses	Blow Molding Applications		
Processing Method	Blow Molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.953	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	0.35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	25.5	MPa	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

