

GAPEKK™ 3230GF

Polyetherketoneketone

Gharda Chemicals Ltd.

Message:

Product Details: Ultra high performance thermoplastic polymer, 30% glass fiber reinforced in Polyether Ketone, semi-crystalline granules suitable for injection molding, easy flow, Beige in color.

Application Areas: Suitable for high temperature applications, where higher strength in load-bearing applications is required. Chemically resistant to aggressive environments, suitable for sterilization for medical and food contact applications.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Food Contact Acceptable		
	Good Chemical Resistance		
	Good Flow		
	Good Sterilizability		
	Good Strength		
	High Heat Resistance		
	Semi Crystalline		
Uses	High Temperature Applications		
	Medical/Healthcare Applications		
	Non-specific Food Applications		
Appearance	Beige		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.50	g/cm ³	
Molding Shrinkage ¹			
Flow	0.30	%	
Across Flow	0.10	%	
Water Absorption (Equilibrium)	0.040	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	91		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	11500	MPa	ASTM D638
Tensile Strength (Yield, 23°C)	170	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.0 to 3.0	%	ASTM D638
Flexural Modulus (23°C)	11.9	MPa	ASTM D790
Flexural Strength (23°C)	260	MPa	ASTM D790
Compressive Strength	167	MPa	ASTM D695

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	60	J/m	ASTM D256
Unnotched Izod Impact (23°C)	610	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	372	°C	ASTM D648
Continuous Use Temperature	300	°C	UL 746B
Glass Transition Temperature	176	°C	ASTM D3418
Melting Temperature	396	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0 to 6.0	hr	
Hopper Temperature	60.0 to 80.0	°C	
Nozzle Temperature	435	°C	
Processing (Melt) Temp	400 to 435	°C	
Mold Temperature	200 to 220	°C	
NOTE			
1.	435°C nozzle, 220°C Mold		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

