

# VITAMIDE® BR15OR6337

Polyamide 6  
Jackdaw Polymers

Message:

VITAMIDE® BR15OR6337 is a Polyamide 6 (Nylon 6) product filled with 25% glass fiber. It is available in Europe. Primary characteristic: flame rated.

| General Information               |                                  |                   |                        |
|-----------------------------------|----------------------------------|-------------------|------------------------|
| Filler / Reinforcement            | Glass Fiber,25% Filler by Weight |                   |                        |
| Appearance                        | Orange                           |                   |                        |
| Forms                             | Pellets                          |                   |                        |
| Physical                          | Nominal Value                    | Unit              | Test Method            |
| Specific Gravity                  | 1.33                             | g/cm <sup>3</sup> | ASTM D792, ISO 1183    |
| Water Absorption (23°C, 24 hr)    | 1.1                              | %                 | ASTM D570, ISO 62      |
| Mechanical                        | Nominal Value                    | Unit              | Test Method            |
| Tensile Strength (Break)          | 135                              | MPa               | ASTM D638, ISO 527-2   |
| Tensile Elongation (Break)        | 3.5                              | %                 | ASTM D638, ISO 527-2   |
| Flexural Modulus                  | 7000                             | MPa               | ASTM D790, ISO 178     |
| Flexural Stress                   |                                  |                   |                        |
| --                                | 185                              | MPa               | ISO 178                |
| Break                             | 185                              | MPa               | ASTM D790              |
| Thermal                           | Nominal Value                    | Unit              | Test Method            |
| Deflection Temperature Under Load |                                  |                   |                        |
| 0.45 MPa, Unannealed              | 212                              | °C                | ASTM D648, ISO 75-2/B  |
| 1.8 MPa, Unannealed               | 200                              | °C                | ASTM D648, ISO 75-2/A  |
| Melting Temperature               | 218                              | °C                | ASTM D2117, ISO 1218   |
| Electrical                        | Nominal Value                    | Unit              | Test Method            |
| Volume Resistivity                | 1.0E+15                          | ohms·cm           | ASTM D257, IEC 60093   |
| Dielectric Strength               | 35                               | kV/mm             | ASTM D149, IEC 60243-1 |
| Comparative Tracking Index        |                                  |                   |                        |
| Solution A                        | 550                              | V                 | IEC 60112              |
| -- 1                              | 550                              | V                 | ASTM D3638             |
| Flammability                      | Nominal Value                    | Unit              | Test Method            |
| Flame Rating                      | HB                               |                   | UL 94                  |
| Oxygen Index                      | 24                               | %                 | ASTM D2863, ISO 4589-2 |
| NOTE                              |                                  |                   |                        |

1. Solution A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

