

# ICORENE® 1613 BK85

Linear Medium Density Polyethylene

ICO Polymers EMEA, A Division of A. Schulman

## Message:

ICORENE® 1613 BK85 is a hexene linear medium density polyethylene specifically developed for use in rotational moulding.

ICORENE® 1613 BK85 is designed for applications requiring good processability, stiffness and toughness. This product is particularly suitable for the production of diesel fuel tanks.

TUV ECE R34 tested

General Information			
Additive	UV Stabilizer		
Features	Good Impact Resistance		
	Good Processability		
	Good Stiffness		
	Good Toughness		
	Good UV Resistance		
	Hexene Comonomer		
Uses	Fuel Tanks		
Appearance	Black		
Forms	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.938	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 100% Igepal)	> 1000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	850	MPa	ASTM D638
Tensile Strength (Yield)	20.0	MPa	ASTM D638
Tensile Elongation (Break)	> 1000	%	ASTM D638
Flexural Modulus	750	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Drop Impact Resistance <sup>1</sup> (-20°C)	> 200	J/cm	Internal Method
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	65.0	°C	ISO 75-2/B
NOTE			

1. Based on ISO 6603

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

