

CALIBRE™ 891-10

Polycarbonate Resin

Trinseo

Message:

CALIBRE™ 891-10 Series provides superior ignition resistance in opaque applications. The CALIBRE 891-10 series products are available in 2 additive packages: CALIBRE 891: Mold release, CALIBRE 893: Mold release and UV stabilizer.

Main Characteristics:

Underwriters Laboratory Inc. (UL)

Applications:

Electronics

Business equipment

Appliances

General Information			
UL YellowCard	E54680-469984	E54680-469985	E206114-228289
Additive	Mold Release		
Features	Flame Retardant		
Uses	Appliances		
	Business Equipment		
	Electrical/Electronic Applications		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792, ISO 1183/A
--	1200	kg/m ³	ISO 1183 ¹
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238, ISO 1133
Melt volume-flow rate (300°C/1.2 kg)	8.00	cm ³ /10min	ISO 1133 ²
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955, ISO 294-4
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570, ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	59		
R-Scale	123		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ³	2380	MPa	ASTM D638
--	2380	MPa	ISO 527-2/50
--	2300	MPa	ISO 527-2 ⁴
Tensile Strength			

Yield ⁵	61.4	MPa	ASTM D638
Yield	61.0	MPa	ISO 527-2/50
Yield	60.0	MPa	ISO 527-2 ⁶
Break ⁷	58.6	MPa	ASTM D638
Break	59.0	MPa	ISO 527-2/50
Tensile Strain			
Yield	6.0	%	ISO 527-2 ⁸
Break ⁹	120	%	ASTM D638
Break	120	%	ISO 527-2/50
Nominal strain at break	> 50	%	ISO 527-2 ¹⁰
Flexural Modulus			
-- ¹¹	2330	MPa	ASTM D790
--	2330	MPa	ISO 178
Flexural Strength			
-- ¹²	97.9	MPa	ASTM D790
--	98.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy notched impact strength			ISO 179/1eA ¹³
-30°C	15.0	kJ/m ²	
23°C	30.0	kJ/m ²	
Charpy impact strength			ISO 179/1eU ¹⁴
-30°C	No Break		
23°C	No Break		
Notched Izod Impact			
23°C	690	J/m	ASTM D256
23°C	68	kJ/m ²	ISO 180/A
Instrumented Dart Impact ¹⁵ (23°C, Total Energy)	62.1	J	ASTM D3763
Tensile Impact Strength	630	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa)	127	°C	ISO 75-2 ¹⁶
Vicat Softening Temperature (50°C/h, B (50N))	151	°C	ISO 306 ¹⁷
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2 ¹⁸
Flammability	Nominal Value	Unit	Test Method
Burning Behav. at 1.6mm nom. thickn. (1.60 mm, UL)	V-0		ISO 1210 ¹⁹
Burning Behav. at thickness h (3.20 mm, UL)	V-0		ISO 1210 ²⁰
Burning Behav. 5V at thickness h (3.20 mm, UL)	5VA		ISO 10351 ²¹
Oxygen index	36	%	ISO 4589-2 ²²
NOTE			

1.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
2.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
3.	51 mm/min
4.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
5.	51 mm/min
6.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
7.	51 mm/min
8.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
9.	51 mm/min
10.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
11.	Method I (3 point load), 2.0 mm/min
12.	Method I (3 point load), 2.0 mm/min
13.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
14.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
15.	3.39 m/sec
16.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
17.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
18.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
19.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
20.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
21.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

22.

Tested in accordance with ISO
10350. 23°C/50%r.h. unless
otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

