

Ronalen M25

Polypropylene
Roonamid a.s.

Message:

Polypropylene, type reinforced with 25% micropulverized talc, natural, optimal flow properties. Suitable for injection mouldings with increased requirements to rigidity and strength.

General Information			
Filler / Reinforcement	Talc,25% Filler by Weight		
Features	Good Strength		
	High Flow		
	High Rigidity		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	31.0	MPa	
Break	27.0	MPa	
Flexural Modulus	2700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	23	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	157	°C	ISO 306
Injection	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Suggested Max Moisture	0.10	%	
Processing (Melt) Temp	230 to 240	°C	
Mold Temperature	40.0 to 60.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

