

TORZEN® G5000HSL NC01

Polyamide 66
INVISTA Engineering Polymers

Message:

TORZEN® G5000HSL NC01 is a 50% glass reinforced, heat stabilized, natural, PA66 resin suitable for many injection molding applications where high tensile strength and dimensional stability are needed.

General Information			
UL YellowCard	E333734-101729709		
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Dimensional Stability		
	Good Mold Release		
	Heat Stabilized		
	High Tensile Strength		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	2.3	g/10 min	ASTM D1238
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	0.80 to 0.90	%	
Flow : 2.00 mm	0.20 to 0.30	%	
Water Absorption			ISO 62
23°C, 24 hr	0.65	%	
Equilibrium, 23°C, 50% RH	1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	16900	MPa	ISO 527-2
Tensile Stress (Break)	247	MPa	ISO 527-2
Tensile Strain (Break)	2.4	%	ISO 527-2
Flexural Modulus	16700	MPa	ISO 178
Flexural Stress	350	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	14	kJ/m²	
23°C	16	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179

-30°C	100	kJ/m ²	
23°C	130	kJ/m ²	
Notched Izod Impact Strength (23°C)	13	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	255	°C	ISO 75-2/A
Melting Temperature	262	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.080 to 0.18	%	
Rear Temperature	250 to 270	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	270 to 290	°C	
Nozzle Temperature	270 to 290	°C	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	50.0 to 90.0	°C	
Back Pressure	0.200 to 1.00	MPa	
Cushion	4.00 to 6.00	mm	
Vent Depth	7.0E-3 to 0.040	mm	
Screw Speed	Low rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

