

# AMTOPP BA25

Polypropylene  
Inteplast Group

## Message:

General Purpose CoEx Heat Sealable  
BIAXIALLY ORIENTED POLYPROPYLENE FILM TWO SIDE SEALABLE FOR FOOD PACKAGING

General Information	
---------------------	--

Uses	Film Food Packaging
------	------------------------

Physical	Nominal Value	Unit
----------	---------------	------

Dimensional Stability		
Across Flow, 130°C <sup>1</sup>	< 3.0	%
Flow, 130°C <sup>2</sup>	< 5.0	%

Mechanical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Coefficient of Friction (Dynamic)	0.20		ASTM D1894
-----------------------------------	------	--	------------

Films	Nominal Value	Unit	Test Method
-------	---------------	------	-------------

Film Thickness - Tested	25	µm	
Tensile Strength			ASTM D882
MD : Yield	117	MPa	
TD : Yield	207	MPa	
Tensile Elongation			ASTM D882
MD : Break	190	%	
TD : Break	70	%	

Water Vapor Transmission Rate (38°C, 90% RH)	5.4	g/m <sup>2</sup> /24 hr	ASTM F1249
--	-----	-------------------------	------------

Yield <sup>3</sup>	44.1	m <sup>2</sup> /kg	
--------------------	------	--------------------	--

Heat Seal Temperature <sup>4</sup>			
Treated Side	121	°C	
Untreated side	104	°C	

Surface Energy	38	dyne/cm	ASTM D2578
----------------	----	---------	------------

Optical	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Gloss (45°)	85		ASTM D2457
Haze	2.0	%	ASTM D1003

NOTE
------

1.	5 minutes
2.	5 minutes
3.	Internal Method
4.	1/2 sec, 30 PSI

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

