

DOW™ LDPE 601C

Low Density Polyethylene Resin

The Dow Chemical Company

Message:

DOW™ LDPE 601C is a Low Density Polyethylene Resin material. It is available in Latin America.

Typical application of DOW™ LDPE 601C: Food Contact Applications

General Information			
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.16	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	µm	
Tensile Strength			ASTM D882
MD : Yield,38 µm	12.0	MPa	
TD : Yield,38 µm	12.0	MPa	
MD : Break, 38 µm	27.0	MPa	
TD : Break, 38 µm	27.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 38 µm	350	%	
TD : Break, 38 µm	600	%	
Dart Drop Impact (38 µm)	190	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 38 µm	250	g	
TD : 38 µm	110	g	
Extrusion	Nominal Value	Unit	
Melt Temperature	165	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT