

# Lumiplas® LD7530

Polycarbonate

LG Chem Ltd.

## Message:

Description

Light diffusion

Application

(LED) Lamp Cover, Signboard, Lighting decoration of electronic device

| General Information |                                    |
|---------------------|------------------------------------|
| Features            | Good Light Diffusion               |
| Uses                | Lighting Applications              |
|                     | Electrical/Electronic Applications |
|                     | Illumination diffuser              |
|                     | Lighting device                    |
| Processing Method   | Extrusion                          |
|                     | Injection molding                  |

| Physical                                                         | Nominal Value | Unit              | Test Method |
|------------------------------------------------------------------|---------------|-------------------|-------------|
| Specific Gravity                                                 | 1.20          | g/cm <sup>3</sup> | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)                         | 11            | g/10 min          | ASTM D1238  |
| Molding Shrinkage - Flow (3.20 mm)                               | 0.50 - 0.80   | %                 | ASTM D955   |
| Hardness                                                         | Nominal Value | Unit              | Test Method |
| Rockwell Hardness (R-Scale)                                      | 118           |                   | ASTM D785   |
| Mechanical                                                       | Nominal Value | Unit              | Test Method |
| Tensile Strength <sup>1</sup> (Break, 3.20 mm)                   | 61.8          | MPa               | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break, 3.20 mm)                 | > 100         | %                 | ASTM D638   |
| Flexural Modulus <sup>3</sup> (6.40 mm)                          | 2260          | MPa               | ASTM D790   |
| Flexural Strength <sup>4</sup> (Yield, 6.40 mm)                  | 93.2          | MPa               | ASTM D790   |
| Impact                                                           | Nominal Value | Unit              | Test Method |
| Notched Izod Impact (23°C, 3.20 mm)                              | 780           | J/m               | ASTM D256   |
| Thermal                                                          | Nominal Value | Unit              | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm) | 130           | °C                | ASTM D648   |
| CLTE - Flow                                                      | 6.8E-5        | cm/cm/°C          | ASTM D696   |
| RTI Elec                                                         | 80.0          | °C                | UL 746      |
| RTI Imp                                                          | 80.0          | °C                | UL 746      |
| RTI                                                              | 80.0          | °C                | UL 746      |
| Flammability                                                     | Nominal Value |                   | Test Method |
| Flame Rating                                                     |               |                   | UL 94       |

|                                                                                                                                                            |               |       |             |
|------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------|-------|-------------|
| 0.800 mm                                                                                                                                                   | V-2           | UL 94 |             |
| 1.60 mm                                                                                                                                                    | V-2           | UL 94 |             |
| Additional Information                                                                                                                                     | Nominal Value | Unit  | Test Method |
| Transparency (1.00 mm)                                                                                                                                     | 55            | %     | JIS K7361   |
| Minimum Moisture Content                                                                                                                                   | 0.020         | %     |             |
| Injection                                                                                                                                                  | Nominal Value | Unit  |             |
| Drying Temperature                                                                                                                                         | 100 - 200     | °C    |             |
| Drying Time                                                                                                                                                | 3.0 - 4.0     | hr    |             |
| Rear Temperature                                                                                                                                           | 260 - 280     | °C    |             |
| Middle Temperature                                                                                                                                         | 280 - 300     | °C    |             |
| Front Temperature                                                                                                                                          | 290 - 310     | °C    |             |
| Nozzle Temperature                                                                                                                                         | 290 - 310     | °C    |             |
| Processing (Melt) Temp                                                                                                                                     | 300 - 320     | °C    |             |
| Mold Temperature                                                                                                                                           | 80.0 - 120    | °C    |             |
| Back Pressure                                                                                                                                              | 0.981 - 3.92  | MPa   |             |
| Screw Speed                                                                                                                                                | 40 - 70       | rpm   |             |
| Extrusion                                                                                                                                                  | Nominal Value | Unit  |             |
| Drying Temperature                                                                                                                                         | 100 - 120     | °C    |             |
| Drying Time                                                                                                                                                | 3.0 - 4.0     | hr    |             |
| Cylinder Zone 1 Temp.                                                                                                                                      | 260 - 280     | °C    |             |
| Cylinder Zone 2 Temp.                                                                                                                                      | 270 - 300     | °C    |             |
| Cylinder Zone 3 Temp.                                                                                                                                      | 270 - 300     | °C    |             |
| Cylinder Zone 4 Temp.                                                                                                                                      | 270 - 300     | °C    |             |
| Adapter Temperature                                                                                                                                        | 280 - 300     | °C    |             |
| Melt Temperature                                                                                                                                           | 300 - 320     | °C    |             |
| Die Temperature                                                                                                                                            | 260 - 295     | °C    |             |
| Extrusion instructions                                                                                                                                     |               |       |             |
| Minimum Moisture Content: 0.02%Roll Stack Temperature - Top: 120-150°CRoll Stack Temperature - Middle: 120-150°CRoll Stack Temperature - Bottom: 120-150°C |               |       |             |
| NOTE                                                                                                                                                       |               |       |             |
| 1.                                                                                                                                                         | 50 mm/min     |       |             |
| 2.                                                                                                                                                         | 50 mm/min     |       |             |
| 3.                                                                                                                                                         | 15 mm/min     |       |             |
| 4.                                                                                                                                                         | 15 mm/min     |       |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

