

GELOY™ HRA170 resin

Acrylonitrile Styrene Acrylate + PC
SABIC Innovative Plastics Europe

Message:

GELOY HRA170 is a high heat resistant ASA+PC. It shows high impact retention, which can be positioned for various outdoor and indoor applications requiring superior heat aging properties and colour stability.

General Information			
Features	Good Color Stability		
	Good Heat Aging Resistance		
	High Heat Resistance		
	High Impact Resistance		
Uses	Outdoor Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	17.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow ¹	0.40 to 0.60	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.60	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Ball Indentation Hardness (H 358/30)	106	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2/1
Tensile Stress			
Yield	55.0	MPa	ISO 527-2/5
Yield	62.0	MPa	ISO 527-2/50
Break	60.0	MPa	ISO 527-2/5
Break	62.0	MPa	ISO 527-2/50
Tensile Strain			
Yield	5.0	%	ISO 527-2/5
Yield	4.0	%	ISO 527-2/50
Break	130	%	ISO 527-2/5
Break	> 50	%	ISO 527-2/50
Flexural Modulus ²	2400	MPa	ISO 178
Flexural Stress	85.0	MPa	ISO 178

Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	95.0	mg	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³			ISO 179/1eA
-30°C	12	kJ/m ²	
23°C	60	kJ/m ²	
Notched Izod Impact Strength ⁴			ISO 180/1A
-30°C	15	kJ/m ²	
23°C	45	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵			
0.45 MPa, Unannealed, 100 mm Span	121	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	112	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	129	°C	ISO 306/B50
--	132	°C	ISO 306/B120
CLTE - Flow (23 to 60°C)	8.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.20	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength (3.20 mm, in Oil)	17	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	2.80		IEC 60250
Dissipation Factor (1 MHz)	0.013		IEC 60250
Comparative Tracking Index	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm, Testing by SABIC)	HB		UL 94
Glow Wire Flammability Index (3.20 mm)	750	°C	IEC 60695-2-12
Oxygen Index	22	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	230 to 260	°C	
Middle Temperature	250 to 290	°C	
Front Temperature	250 to 290	°C	
Nozzle Temperature	240 to 280	°C	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	60.0 to 90.0	°C	
NOTE			
1.	Tensile Bar		

2.	2.0 mm/min
3.	80*10*4 sp=62mm
4.	80*10*4
5.	120*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

