

Chiao Fu PA6 MC212G20 NAT

Polyamide 6

Chiao Fu Enterprises Co., Ltd.

Message:

Chiao Fu PA6 MC212G20 NAT is a Polyamide 6 (Nylon 6) product filled with 20% glass fiber. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E135541-222596		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
RoHS Compliance	RoHS Compliant		
UL File Number	E135541		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	< 0.35	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	118	MPa	ASTM D638
Tensile Elongation (Break)	< 5.0	%	ASTM D638
Flexural Modulus	5590	MPa	ASTM D790
Flexural Strength	186	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	205	°C	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm, ALL)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

