

# Royalcast® 3105

Polyurethane (Polyether based)

Chemtura

## Message:

ROYALCAST 3105 is a two-component system that has outstanding processing characteristics. These include:

- Low viscosity at room temperature
- Easy mixing
- Adjustable pot life (1 - 60 min.)
- Low shrinkage

Additionally, because ROYALCAST 3105 has a moderate demold time, mold turnabout can be high, thus minimizing tooling and direct labor cost. In summary, ROYALCAST 3105 with its good balance of physical properties and processing characteristics is an attractive material candidate for numerous end-use applications that require rigidity.

General Information			
Features	High Rigidity		
	Low Shrinkage		
	Low Viscosity		
Appearance	White		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	1.0	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 20°C)	111		ASTM D785
Durometer Hardness			ASTM D2240
Shore D, 100°C	68		
Shore D, 70°C	74		
Shore D, 20°C	77		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	40.0	MPa	ASTM D638
Tensile Elongation (Break)	25	%	ASTM D638
Flexural Modulus	1310	MPa	ASTM D790
Flexural Strength	51.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	37	J/m	
20°C	43	J/m	
Unnotched Izod Impact			ASTM D256
-40°C	750	J/m	
20°C	960	J/m	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	90.0	°C	ASTM D648
CLTE - Flow	1.1E-4	cm/cm/°C	ASTM D696
Thermoset	Nominal Value	Unit	
Thermoset Components			
Hardener	Mix Ratio by Weight: 29		
Resin	Mix Ratio by Weight: 100		
Pot Life	1.0	min	
Demold Time	8.0	min	
Post Cure Time (100°C)	16	hr	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

