

Adell Polyamide AW-37

Polyamide 66

Adell Plastics, Inc.

Message:

Adell Polyamide AW-37 is a Polyamide 66 (Nylon 66) material filled with 33% glass fiber. It is available in North America.

Important attributes of Adell Polyamide AW-37 are:

Flame Rated

Good Aesthetics

General Information			
UL YellowCard	E44974-235700		
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Features	Good Surface Finish		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36 to 1.37	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Water Absorption (24 hr)	1.1	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	89		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	186	MPa	ASTM D638
Tensile Elongation (Break)	3.0 to 4.0	%	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength	193	MPa	ASTM D790
Compressive Strength	165	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	216	°C	
1.8 MPa, Unannealed	204	°C	
Melting Temperature	210 to 221	°C	
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

