

Durethan® AKV 15 FN 00 000000

Polyamide 66

LANXESS GmbH

Message:

PA 66, 12 % glass fibers, injection molding, halogen free flame retardant

General Information				
Filler / Reinforcement		Glass Fiber, 12% Filler by Weight		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.28	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (270°C/2.16 kg)	25.0	--	cm ³ /10min	ISO 1133
Molding Shrinkage				ISO 2577
Across Flow : 270°C, 2.00 mm ¹	1.0	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.10	--	%	
Flow : 270°C, 2.00 mm ³	0.60	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	5.5	--	%	
Equilibrium, 23°C, 50% RH	1.8	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	6500	3600	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	90.0	50.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.3	5.5	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	6400	3300	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	150	90.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.3	5.5	%	ISO 178/A
ISO Shortname	PA 66, GFHR, 14-060, GF12 ISO-1043:PA GF FR (30+40)			ISO 1874
Residual Moisture Content	0.030 to 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	40	45	kJ/m ²	ISO 179/1eU

Notched Izod Impact Strength (23°C)	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	35	40	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	245	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	--	°C	ISO 75-2/A
Vicat Softening Temperature	225	--	°C	ISO 306/B120
Melting Temperature ⁸	262	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 0	--		UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.400 mm	V-0	--		
0.750 mm	V-0	--		
1.50 mm	V-0	--		
3.00 mm	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.400 mm	960	--	°C	
0.800 mm	960	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	265 to 285		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

