

TAROLON 2500 G6

Polycarbonate

Taro Plast S.p.A.

Message:

Polycarbonate medium viscosity, 30% glass fiber reinforced, very good mechanical properties also at high temperature, good dimensional stability, low shrinkage.
Available: all colors, UV stabilized (L), release agent (W).

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Mold Release		
	UV Stabilizer		
Features	Good Dimensional Stability		
	Good Mold Release		
	Good UV Resistance		
	Low Shrinkage		
	Medium Heat Resistance		
	Medium Viscosity		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42 to 1.44	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Water Absorption			
23°C, 24 hr	0.050	%	ASTM D570, ISO 62
Saturation	0.20	%	ASTM D570
Saturation, 23°C	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8600	MPa	ASTM D638, ISO 527-2
Tensile Strength (Break)	105	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	3.0	%	ASTM D638, ISO 527-2
Flexural Modulus	8500	MPa	ASTM D790, ISO 178
Flexural Stress			
-- 1	200	MPa	ISO 178
-- 2	185	MPa	ISO 178
Yield	200	MPa	ASTM D790
Break	185	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (23°C)	9.0	kJ/m ²	ASTM D256, ISO 179
Charpy Unnotched Impact Strength ⁴ (23°C)	44	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	140	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	145	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature ⁵	135	°C	IEC 60216
Vicat Softening Temperature	154	°C	ISO 306/A50, ASTM D1525 ⁶
Ball Pressure Test (125°C)	Pass		VDE 0470
CLTE - Flow (-30 to 30°C)	2.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	24	kV/mm	ASTM D149
Comparative Tracking Index (Solution A)	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-1		UL 94
Glow Wire Ignition Temperature (2.00 mm)	850	°C	IEC 60695-2-13
Oxygen Index	32	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature			
--	100 to 110	°C	
Pre-heater	120 to 130	°C	
Drying Time			
--	1.0 to 2.0	hr	
Pre-heater	3.0	hr	
Processing (Melt) Temp	260 to 300	°C	
Mold Temperature	100 to 120	°C	
Injection Rate	Fast		
NOTE			
1.	Yield		
2.	Break		
3.	6x4x50 mm		
4.	6x4x50 mm		
5.	20000 hrs		
6.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

