

Solef® 41308

Polyvinylidene Fluoride
Solvay Specialty Polymers

Message:

Solef® 41308/0001 PVDF is specifically developed for coextrusion.

General Information			
Processing Method	Coextrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.78	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/2.16 kg	6.0 to 8.0	g/10 min	
230°C/5.0 kg	18 to 24	g/10 min	
Water Absorption ¹ (23°C, 24 hr)	< 0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ² (23°C)	1900	MPa	ASTM D638
Tensile Strength ³			ASTM D638
Yield, 23°C	48.0	MPa	
Break, 23°C	30.0	MPa	
Tensile Elongation ⁴ (Yield, 23°C)	7.0	%	ASTM D638
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.31		
vs. Itself - Static	0.32		
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-10 Wheel)	8.00	mg	ISO 5470-1
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵ (23°C)	8.5	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	169	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	136	°C	ASTM D3418
Crystallization Heat	51.6	J/g	ASTM D3418
Heat of Fusion ⁶	52.7	J/g	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+14	ohms · cm	ASTM D257
NOTE			
1.	Method 1		
2.	1.0 mm/min		
3.	50 mm/min		
4.	50 mm/min		

5.	4 mm thick, 2 m/s
6.	80°C to end of melting

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

