

Iupilon® EHR3150

Polycarbonate

Mitsubishi Engineering-Plastics Corp

Message:

Iupilon® EHR3150 is a Polycarbonate (PC) material. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of Iupilon® EHR3150 are:

Flame Rated

Halogen Free

High Flow

General Information			
UL YellowCard	E41179-100170266		
Features	Bromine Free		
	High Flow		
	High Reflectivity		
	Low (to None) Phosphorus Content		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	46	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	43.0	cm ³ /10min	ISO 1133
Molding Shrinkage			
Across Flow : 3.20 mm	0.40 to 0.60	%	
Flow : 3.20 mm	0.40 to 0.60	%	
Water Absorption (Saturation, 23°C)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2
Tensile Stress (Yield)	54.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.1	%	ISO 527-2
Nominal Tensile Strain at Break	13	%	ISO 527-2
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress	89.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	134	°C	ISO 75-2/B
1.8 MPa, Unannealed	117	°C	ISO 75-2/A

CLTE			ISO 11359-2
Flow	6.2E-5	cm/cm/°C	
Transverse	6.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	6.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0 to 8.0	hr	
Rear Temperature	240 to 260	°C	
Middle Temperature	250 to 270	°C	
Front Temperature	260 to 280	°C	
Nozzle Temperature	260 to 280	°C	
Mold Temperature	70.0 to 100	°C	
Injection Pressure	50.0 to 150	MPa	
Screw Speed	50 to 100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

