

Lupol® HM5302W

Compounded Polypropylene

LG Chem Ltd.

Message:

Description

Good Weatherability, High Impact

Application

Automotive Interior Parts

General Information			
Filler / Reinforcement	Mineral,30% Filler by Weight		
Features	Good Weather Resistance		
	High Impact Resistance		
Uses	Automotive Interior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.70 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	21.6	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	45	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	2840	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 6.40 mm)	32.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.40 mm)	210	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵ (0.45 MPa, Unannealed, 3.20 mm)	138	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	< 0.010	%	
Rear Temperature	190 to 210	°C	
Middle Temperature	200 to 230	°C	
Front Temperature	200 to 230	°C	
Nozzle Temperature	210 to 230	°C	
Processing (Melt) Temp	200 to 230	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	29.4 to 58.8	MPa	

Screw Speed	30 to 60	rpm
NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	30 mm/min	
4.	30 mm/min	
5.	4.6kg	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

