

Hiprolon® 11 ECN Blue H8L

Polyamide 1012

Arkema

Message:

Hiprolon ® 11 ECN Blue H8L is a polyamide produced from a renewable source. This blue coloured grade is designed for extrusion and recommended for cable sheathing application.

MAIN APPLICATIONS

Cable sheathing.

General Information			
Features	Renewable Resource Content		
Uses	Wire & Cable Applications		
Appearance	Blue		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (235°C/5.0 kg)	5.00	cm³/10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	72		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	45.0	MPa	
Break	61.0	MPa	
Tensile Strain			ISO 527-2
Yield	22	%	
Break	> 200	%	
Flexural Modulus	1170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	15	kJ/m²	
23°C	12	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	190	°C	ISO 11357-3
Additional Information	Nominal Value	Unit	Test Method
ISO Shortname	PA 1012, KHL, 22-010		ISO 1874
Renewable Carbon Conent	> 42	%	ASTM D6866
Extrusion	Nominal Value	Unit	

Drying Temperature	80.0 to 90.0	°C
Drying Time	4.0	hr
Melt Temperature	210 to 260	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

