

Polimid A EM1

Polyamide 66

Poliblend S.p.a.

Message:

Polimid A EM1 is a Polyamide 66 (Nylon 66) material. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Primary attribute of Polimid A EM1: Flame Rated.

General Information			
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Molding Shrinkage	1.6 to 2.0	%	
Water Absorption (23°C, 24 hr)	0.90	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	6.5	%	
Break	65	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	12	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	195	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	°C	ISO 75-2/A
Continuous Use Temperature ¹	80.0	°C	
Vicat Softening Temperature	252	°C	ISO 306/A120
Ball Pressure Test (165°C)	Pass		IEC 60695-10-2
Melting Temperature	260	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
3.20 mm	HB		
Glow Wire Flammability Index (2.00 mm)	800	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	

Drying Time	> 3.0	hr
Processing (Melt) Temp	260 to 280	°C
Mold Temperature	60.0 to 80.0	°C

NOTE

1. Without Load

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

