

AKROMID® B3 GF 10 1 L natural (5011)

Polyamide 6 + PP
AKRO-PLASTIC GmbH

Message:

AKROMID® B3 GF 10 1 L natural (5011) is a 10% glass fibre reinforced and heat stabilised polyamide-blend with a reduced density compared to standard PA6 GF 15
Applications are mainly technical components in the automotive and electronic industry, where a weight and cost reduction is required

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Low Density		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Appearance	Natural Color		
Resin ID (ISO 1043)	PA6 + PP GF10		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4000	MPa	ISO 527-2/1
Tensile Stress (Break)	90.0	MPa	ISO 527-2/5
Tensile Strain (Break)	3.9	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.5	kJ/m²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	220	°C	DIN EN 11357-1
Flammability	Nominal Value	Unit	Test Method
Burning Rate ² (1.00 mm)	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Reinforcement Content	10	%	ISO 1172
NOTE			
1.	10 K/min, DSC		
2.	>1 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

