

LIHAN® P620

Polypropylene
Nanjing Lihan Chemical Co., Ltd.

Message:
LIHAN® P620 is a Polypropylene product. It can be processed by injection molding and is available in Asia Pacific. Primary characteristic: flame rated.

General Information			
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ISO 1183
Molding Shrinkage	1.2 to 1.6	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	25.0	MPa	ISO 527-2
Tensile Strain (Break)	250	%	ISO 527-2
Flexural Modulus	1050	MPa	ISO 178
Flexural Stress	30.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	45	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
Melting Temperature	160	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	19	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 230	°C	
Mold Temperature	40.0 to 50.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

