

Badadur® PBT8 GF30 FR

Polybutylene Terephthalate

Bada AG

Message:

Medium viscosity, 30 % glass fibres reinforced, flame retardent standard injection moulding grade with very good mechanical properties

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
	Medium Viscosity		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
Water Absorption			ISO 62
Saturation, 23°C	0.32	%	
Equilibrium, 23°C, 50% RH	0.13	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	7500	MPa	ISO 527-2
Tensile Stress ² (Break, 23°C)	115	MPa	ISO 527-2/5
Tensile Strain ³ (Break, 23°C)	2.8	%	ISO 527-2/5
Flexural Stress ⁴ (23°C)	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵			ISO 179/1eA
-30°C	7.5	kJ/m ²	
23°C	9.0	kJ/m ²	
Charpy Unnotched Impact Strength ⁶			ISO 179/1eU
-30°C	50	kJ/m ²	
23°C	50	kJ/m ²	
Notched Izod Impact Strength ⁷			ISO 180/1A
-30°C	7.0	kJ/m ²	
23°C	8.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁸			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	°C	ISO 75-2/A
Melting Temperature (DSC) ⁹	223	°C	ISO 3146
CLTE ¹⁰			DIN 53752
Flow	4.2E-5	cm/cm/°C	
Transverse	1.0E-4	cm/cm/°C	

Maximum Service Temperature			IEC 216
20000 hrs	135	°C	
some hours	170	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ¹¹	> 1.0E+14	ohms	IEC 60093
Volume Resistivity ¹²	> 1.0E+16	ohms·cm	IEC 60093
Electric Strength ¹³	28	kV/mm	IEC 60243-1
Relative Permittivity ¹⁴ (1 MHz)	3.60		IEC 60250
Dissipation Factor ¹⁵ (1 MHz)	0.017		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating ¹⁶ (1.60 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	245 to 265	°C	
Mold Temperature	60.0 to 100	°C	
NOTE			
1.	Test Specimen accordng to ISO 3167, Type A		
2.	Test Specimen accordng to ISO 3167, Type A		
3.	Test Specimen accordng to ISO 3167, Type A		
4.	80x10x4 mm		
5.	80x10x4 mm		
6.	80x10x4 mm		
7.	80x10x4 mm		
8.	110x10x4 mm		
9.	10 K/min, Compound for moulding		
10.	>= 10x10x4 mm		
11.	80x80x1 mm		
12.	80x80x1 mm		
13.	80x80x1 mm		
14.	80x80x1 mm		
15.	80x80x1 mm		
16.	125x13x1.6		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

