

LG ABS XR440

Acrylonitrile Butadiene Styrene

LG Chem Ltd.

Message:

Description
Heat Resistance, Low Emission
Applications
Automotives Interior housing (Glove Box Etc)

General Information			
Features	High Heat Resistance		
	Low Emissions		
Uses	Automotive Applications		
	Automotive Interior Parts		
	Housings		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	113		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	49.0	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	20	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2550	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	78.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	59	J/m	
-30°C, 6.40 mm	49	J/m	
23°C, 3.20 mm	130	J/m	
23°C, 6.40 mm	120	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	109	°C	
1.8 MPa, Unannealed, 6.40 mm	102	°C	
Vicat Softening Temperature	110	°C	ASTM D1525 ⁵

Injection	Nominal Value	Unit
Drying Temperature	80.0 to 90.0	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	< 0.070	%
Rear Temperature	180 to 200	°C
Middle Temperature	200 to 220	°C
Front Temperature	220 to 230	°C
Nozzle Temperature	220 to 230	°C
Processing (Melt) Temp	190 to 210	°C
Mold Temperature	40.0 to 60.0	°C
Back Pressure	0.981 to 2.94	MPa

NOTE

1. 50 mm/min
2. 50 mm/min
3. 15 mm/min
4. 15 mm/min
5. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT