

POLYLAC® PA-726M

Acrylonitrile Butadiene Styrene

CHI MEI CORPORATION

Message:

POLYLAC® PA-726M is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E56070-245711		
Features	Platable		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.04	g/cm ³	ASTM D792
23°C	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	2.1	g/10 min	
220°C/10.0 kg	26	g/10 min	
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)			ISO 1133
	27.0	cm ³ /10min	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Ball Indentation Hardness (H 358/30)	97.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Yield	42.0	MPa	ISO 527-2/50
Break	35.0	MPa	ISO 527-2/50
3.00 mm ¹	38.2	MPa	ASTM D638
Tensile Elongation			
Break, 3.00 mm ²	30	%	ASTM D638
Break	37	%	ISO 527-2/50
Flexural Modulus			
6.00 mm ³	2140	MPa	ASTM D790
-- ⁴	2050	MPa	ISO 178
Flexural Strength			
6.00 mm ⁵	57.9	MPa	ASTM D790
-- ⁶	62.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength	27	kJ/m ²	ISO 179
Notched Izod Impact			
23°C, 3.00 mm	260	J/m	ASTM D256
23°C, 6.00 mm	250	J/m	ASTM D256
-30°C	12	kJ/m ²	ISO 180/1A
23°C	25	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	85.0	°C	ASTM D648
1.8 MPa, Unannealed	80.0	°C	ISO 75-2/A
1.8 MPa, Annealed	100	°C	ASTM D648
1.8 MPa, Annealed	86.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	105	°C	ASTM D1525 ⁷
--	102	°C	ISO 306/A50
--	103	°C	ISO 306/A120
--	95.0	°C	ISO 306/B50
--	98.0	°C	ISO 306/B120
CLTE - Flow	8.0E-5 to 1.0E-4	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	HB		
1.60 mm	HB		
Additional Information	Nominal Value	Unit	
Shrink Ratio	0.30 to 0.60	%	
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	180 to 220	°C	
Middle Temperature	190 to 230	°C	
Front Temperature	190 to 230	°C	
Mold Temperature	30.0 to 70.0	°C	
NOTE			
1.	6.0 mm/min		
2.	6.0 mm/min		
3.	2.8 mm/min		
4.	2.0 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

