

Axiall PVC 8895

Polyvinyl Chloride

Axiall Corporation

Message:

General purpose extrusion compound formulated for good UV light stability.

General Information			
Features	General Purpose		
	Good UV Resistance		
Uses	General Purpose		
Processing Method	Extrusion		
Hardness	Nominal Value		Test Method
Durometer Hardness ¹ (Shore A)	86 to 92		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant	11.0	MPa	ASTM D638
Tensile Strength	18.6	MPa	ASTM D638
Tensile Elongation (Break)	310	%	ASTM D638
Extrusion	Nominal Value	Unit	
Melt Temperature	182	°C	
NOTE			
1.	Delayed		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT