

Celstran® PA66-GF40-02P11/15

Polyamide 66

Celanese Corporation

Message:

Material code according to ISO 1043-1: PA66

Heat stabilized Nylon 66 reinforced by 40 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long.

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection.

The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

General Information			
Filler / Reinforcement	Long glass fiber, 40% filler by weight		
Additive	heat stabilizer		
Features	Low warpage		
	Rigidity, high		
	High strength		
	Impact resistance, good		
	Good creep resistance		
	Low temperature impact resistance		
	Heat resistance, high		
	Thermal Stability		
Uses	Metal substitution		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PA66		
Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
--	13700	MPa	ISO 527-2/1A/1
80°C	9000	MPa	ISO 527-2/1A
Tensile Stress			
Fracture	180	MPa	ISO 527-2/1A/5

80°C	130	MPa	ISO 527-2/1A
Tensile Strain			
Fracture	1.5	%	ISO 527-2/1A/5
Fracture, 80°C	2.0	%	ISO 527-2/1A
Flexural Modulus			ISO 178
23°C	12600	MPa	ISO 178
80°C	8000	MPa	ISO 178
Flexural Stress			ISO 178
23°C	260	MPa	ISO 178
80°C	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	23	kJ/m ²	ISO 179/1eA
23°C	23	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	41	kJ/m ²	ISO 179/1eU
23°C	40	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	35	kJ/m ²	ISO 180/1A
23°C	24	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
1.8 MPa, not annealed	255	°C	ISO 75-2/A
8.0 MPa, not annealed	240	°C	ISO 75-2/C
Melting Temperature ¹	261	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 80.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.15	%	
Hopper Temperature	70.0 - 80.0	°C	
Rear Temperature	265 - 275	°C	
Middle Temperature	275 - 285	°C	
Front Temperature	285 - 295	°C	
Nozzle Temperature	305 - 315	°C	
Processing (Melt) Temp	305 - 315	°C	
Mold Temperature	90.0 - 120	°C	
Injection Pressure	120 - 150	MPa	
Injection Rate	Moderate		
Holding Pressure	50.0 - 80.0	MPa	
Back Pressure	0.00 - 3.00	MPa	
Injection instructions			
Manifold Temperature: 300 to 315°CZone 4 Temperature: 295 to 305°CFeed Temperature: 20 to 50°C			

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

