

ULTEM™ HU1000 resin

Polyether Imide

SABIC Innovative Plastics

Message:

Transparent, standard flow Polyetherimide (Tg 217C). RoHS compliant. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO 10993 or USP Class VI), food contact compliant. UL94 V0 and 5VA listed. EtO and steam sterilizable.

General Information			
Features	Ethylene oxide disinfection		
	Biocompatibility		
	Compliance of Food Exposure		
	Disinfect with steam		
Uses	Drug		
	Medical/nursing supplies		
Agency Ratings	ISO 10993		
	USP Class VI		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	9.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (220°C/5.0 kg)	13.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			
24 hr	0.25	%	ASTM D570
Saturated, 23°C	1.3	%	ISO 62
Equilibrium, 23°C	1.3	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.70	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3580	MPa	ASTM D638
--	3200	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	110	MPa	ASTM D638
Yield	105	MPa	ISO 527-2/5
Fracture ³	90.0	MPa	ASTM D638

Fracture	85.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/5
Fracture ⁵	60	%	ASTM D638
Fracture	60	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁶	3440	MPa	ASTM D790
-- ⁷	3300	MPa	ISO 178
Flexural Stress			
--	160	MPa	ISO 178
Yield, 50.0mm span ⁸	173	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	4.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	55	J/m	ASTM D256
23°C	53	J/m	ASTM D256
-30°C ¹⁰	6.0	kJ/m ²	ISO 180/1A
23°C ¹¹	6.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	1300	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 6.40mm	201	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	215	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	219	°C	ASTM D1525 ¹³
--	215	°C	ISO 306/B50
--	211	°C	ISO 306/B120
Linear thermal expansion coefficient			
Flow: -20 to 150°C	5.6E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	5.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -20 to 150°C	5.4E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	5.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Dielectric Strength			
1.60 mm, in Air	33	kV/mm	ASTM D149
1.60 mm, in Oil	28	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.15		ASTM D150
Dissipation Factor			
1 kHz	1.3E-3		ASTM D150
2.45 GHz	2.5E-3		ASTM D150

Arc Resistance ¹⁴	PLC 5	ASTM D495	
Comparative Tracking Index (CTI)	PLC 4	UL 746	
High Amp Arc Ignition (HAI)	PLC 3	UL 746	
High Voltage Arc Tracking Rate (HVTR)	PLC 2	UL 746	
Hot-wire Ignition (HWI)	PLC 1	UL 746	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	47	%	ASTM D2863
NBS Smoke Density - Flaming, Ds, 4 min	0.700		ASTM E662
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 - 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	332 - 399	°C	
Middle Temperature	338 - 399	°C	
Front Temperature	343 - 399	°C	
Nozzle Temperature	343 - 399	°C	
Processing (Melt) Temp	349 - 399	°C	
Mold Temperature	135 - 163	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	Type 1, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*4 sp=62mm		
10.	80*10*4		
11.	80*10*4		
12.	80*10*4 mm		
13.	标准 B (120°C/h), 载荷2 (50N)		
14.	Tungsten electrode		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHEG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

