

Lucon® CP6062EX

Polycarbonate + ABS

LG Chem Ltd.

Message:

Lucon® CP-6062EX is a Polycarbonate + ABS (PC+ABS) material filled with carbon nano. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding or sheet extrusion.

Important attributes of Lucon® CP-6062EX are:

ESD Protection

Good Processability

Typical application of Lucon® CP-6062EX: Sheet

General Information			
Filler / Reinforcement	Carbon Nano		
Features	ESD Protection		
	Good Processability		
Uses	Sheet		
Processing Method	Injection Molding		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	58.8	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	14	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2750	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	98.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	34	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.40 mm)	110	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4 to 1.0E+6	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	5.0 to 7.0	hr	
Rear Temperature	280 to 300	°C	
Middle Temperature	290 to 310	°C	

Front Temperature	290 to 310	°C
Nozzle Temperature	290 to 310	°C
Processing (Melt) Temp	290 to 310	°C
Mold Temperature	60.0 to 80.0	°C
Back Pressure	0.00 to 0.981	MPa
Screw Speed	40 to 60	rpm

NOTE

- | | |
|----|-----------|
| 1. | 50 mm/min |
| 2. | 50 mm/min |
| 3. | 15 mm/min |
| 4. | 15 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

