# LightSpan® LS1-6140

#### Silicone

#### **NuSil Technology**

#### Message:

From LEDs to fiber optics, NuSil Technology's LightSpan™ brand product line delivers the most comprehensive line of refractive index matching adhesives, encapsulants and thermosets available.

The benefits of silicone include the following:

Thermal Stability

Low Ionic Species

Maintain Optical Clarity (90% minimum @ 400nm)

Low Moisture Absorption (<0.4%)

Optimization for UV Resistance

Adjustable Cure

Low Outgassing

Low Shrinkage, <1%

Low Modulus: Stress reduction for bonding materials with different coefficients of thermal expansion

Gernal Purpose: Optical Adhesives and Elastomers

Comments: LS-6140 with longer work time for dispensing, 80°C minimum cure

| General Information      |                          |      |  |
|--------------------------|--------------------------|------|--|
| Features                 | Good Thermal Stability   |      |  |
|                          | Good UV Resistance       |      |  |
|                          | Low Moisture Absorption  |      |  |
|                          | Low Shrinkage            |      |  |
|                          | Low to No Outgassing     |      |  |
|                          |                          |      |  |
| Uses                     | Adhesives                |      |  |
| Processing Method        | Casting                  |      |  |
|                          | Injection Molding        |      |  |
|                          |                          |      |  |
| Optical                  | Nominal Value            |      |  |
| Refractive Index         | 1.400                    |      |  |
| Thermoset                | Nominal Value            | Unit |  |
| Thermoset Components     |                          |      |  |
| Part A                   | Mix Ratio by Weight: 1.0 |      |  |
| Part B                   | Mix Ratio by Weight: 1.0 |      |  |
| Uncured Properties       | Nominal Value            | Unit |  |
| Viscosity                |                          |      |  |
| 1                        | 2.5                      | Pa·s |  |
| <sup>2</sup>             | 3.5                      | Pa·s |  |
| Curing Time (150°C)      | 1.0                      | hr   |  |
| Cured Properties         | Nominal Value            | Unit |  |
| Shore Hardness (Shore A) | 50                       |      |  |
| Tensile Strength         | 6.21                     | MPa  |  |
|                          |                          |      |  |

| Tensile Elongation at Break | 90     | % |  |
|-----------------------------|--------|---|--|
| NOTE                        |        |   |  |
| 1.                          | Part B |   |  |
| 2.                          | Part A |   |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

