

AIE PA6 50G3ST

Polyamide 6

Asia International Enterprise (Hong Kong) Limited

Message:

AIE PA6 50G3ST is a polyamide 6 (nylon 6) material, which contains a filler of 15% glass fabric reinforcement. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

The main features of AIE PA6 50G3ST are:

flame retardant/rated flame

Good toughness

General Information			
Filler / Reinforcement	Glass fabric reinforcement, 15% filler by weight		
Features	Good toughness		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183
Molding Shrinkage	0.60 - 1.2	%	Internal method
Water Absorption (23°C, 24 hr)	1.2	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	110	MPa	ISO 527-2
Tensile Strain (Break)	7.0	%	ISO 527-2
Flexural Modulus	4000	MPa	ISO 178
Flexural Stress	135	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	26	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	195	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	245 - 260	°C	
Middle Temperature	240 - 250	°C	
Front Temperature	230 - 250	°C	
Nozzle Temperature	250 - 260	°C	
Mold Temperature	50.0 - 110	°C	
Injection Pressure	30.0 - 80.0	MPa	

Holding Pressure	40.0 - 50.0	MPa
Back Pressure	5.00 - 10.0	MPa
Screw Speed	40 - 70	rpm

Injection instructions

Cylinder Temperature 4: 230 to 245°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

