INELEC PCABSFRAS

Polycarbonate + ABS

Infinity LTL Engineered Compounds

Message:

INELEC PCABSFRAS is a Polycarbonate + ABS (PC+ABS) product. It is available in North America. Characteristics include:

Flame Retardant

General Information

Antistatic

Additive	Antistatic		
	Flame Retardant		
Features	Antistatic		
	Flame Retardant		
District.	Nominal Value	Unit	To at Madilla ad
Physical			Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.60 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	41.4	MPa	ASTM D638
Tensile Elongation (Yield)	2.0 to 5.0	%	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	150	J/m	ASTM D256
Unnotched Izod Impact	530 to 640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	96.1	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9 to 1.0E+11	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	243 to 260	°C	
Mold Temperature	51.7 to 82.2	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.051	mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

