

DENKA ABS GR-2000LG

Acrylonitrile Butadiene Styrene

Denka Company Limited

Message:

DENKA ABS GR-2000LG is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Low Gloss

General Information			
Features	Low Gloss		
UL File Number	E49895		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.03	g/cm ³	ASTM D792
23°C	1.03	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	0.50 to 0.70	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	99		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	35.0	MPa	ASTM D638
--	2000	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	37.0	MPa	
Break	29.0	MPa	
Nominal Tensile Strain at Break	51	%	ISO 527-2/50
Flexural Modulus			
-- ²	1900	MPa	ASTM D790
-- ³	1950	MPa	ISO 178
Flexural Strength			
-- ⁴	57.0	MPa	ASTM D790
-- ⁵	61.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	32	kJ/m ²	ISO 179
Notched Izod Impact	340	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed ⁶	86.0	°C	ASTM D648

1.8 MPa, Unannealed	77.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	98.0	°C	ASTM D1525 ⁷
--	97.0	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁸	> 1.0E+16	ohms	JIS K6911
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	180 to 200	°C	
Middle Temperature	200 to 230	°C	
Front Temperature	210 to 260	°C	
Nozzle Temperature	210 to 255	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	0.490 to 0.981	MPa	
Screw Speed	80 to 120	rpm	
NOTE			
1.	5.0 mm/min		
2.	15 mm/min		
3.	2.0 mm/min		
4.	15 mm/min		
5.	2.0 mm/min		
6.	Edgewise		
7.	Loading 2 (50 N)		
8.	23°C, 50% RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT