# NuSil CV-2644

#### Silicone

## **NuSil Technology**

## Message:

Controlled Volatility (CV) Silicone Materials

Silicone's ability to remain elastic at low temperatures and resistant to breakdown at high temperatures offer excellent utility in extraterrestrial environments where materials are repeatedly exposed to extreme temperatures. NuSil's Controlled Volatility (CV) and Ultra Low Outgassing TM (SCV) silicone products are used by leading space programs to provide the much-needed resilient protection they require against contamination and material degradation

Benefits of Silicone Materials for Space Broad Operating Temperature Compensation for CTE Mismatch Protection Against Atomic Oxygen Optically Clear Formulations Flight Legacy

Comments: 0.005 ohm-cm, 1.2 W/m-K

General Information	
Features	Electrically Conductive
	Low to No Outgassing
Uses	Aerospace Applications
	Electrical/Electronic Applications
Agency Ratings	ASTM E 595
	NASA SP-R-0022A

Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	2.2E-4	cm/cm/°C	
Thermal Conductivity	1.2	W/m/K	ASTM E1530
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 20		
Part B	Mix Ratio by Weight: 1.0		
Additional Information	Nominal Value	Unit	
Cure System	Platinum		
Uncured Properties	Nominal Value	Unit	
Color	Tan		
Density	3.38	g/cm³	
Curing Time (150°C)	0.50	hr	
Pot Life	180	min	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore A)	85		
Tensile Strength	3.62	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

