

NILAMID® A3 VNGF30

Polyamide 66

Nilit Plastics

Message:

NILAMID® A3 VNGF30 is a cross linkable Polyamide 66 (Nylon 66) compound, 30% glass fiber reinforced.

This compound is intended for injection molding.

NILAMID® A3 VNGF30 is primarily designed for Electrical and Electronic industry. It is also suitable for Automotive applications.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Crosslinkable		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.36	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	0.80	%	
Flow : 23°C	0.30	%	
Water Absorption			ISO 62
23°C, 24 hr	1.8	%	
Saturation, 23°C	6.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9400	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	193	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	3.0	kJ/m ²	
23°C	8.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
23°C	No Break		
30°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	> 300	°C	ISO 75-2/B
1.8 MPa, Unannealed	> 300	°C	ISO 75-2/A
Continuous Use Temperature ¹	140	°C	IEC 60216
Ball Pressure Test			IEC 60695-10-2
125°C	Pass		

165°C	Pass		
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ²	1.0E+14	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	ohms·cm	IEC 60093
Comparative Tracking Index (3.20 mm, Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
3.20 mm	HB		
Glow Wire Flammability Index (3.20 mm)	960	°C	IEC 60695-2-12
NOTE			
1.	20000 hr		
2.	23°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

