

KOCETAL® K300

Acetal (POM) Copolymer

Kolon Plastics, Inc.

Message:

Kocetal K300 is a general injection molding grade with a good mechanical property for wide range.

General Information			
UL YellowCard	E190675-238633		
Features	General Purpose		
Uses	General Purpose		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60%RH)	0.22	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	64.0	MPa	ASTM D638
Tensile Elongation (Yield, 23°C)	60	%	ASTM D638
Flexural Modulus (23°C)	2500	MPa	ASTM D790
Flexural Strength (23°C)	94.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	67	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	158	°C	
1.8 MPa, Unannealed	110	°C	
Vicat Softening Temperature	162	°C	ASTM D1525
Melting Temperature ¹	166	°C	ASTM D3418
CLTE - Flow	1.3E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant	3.70		ASTM D150

Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT