

# TROSIFOL® Sound Control

Polyvinyl Butyral  
Kuraray Co., Ltd.

Message:

TROSIFOL® Sound Control is a Polyvinyl Butyral (PVB) material. It is available in Asia Pacific, Europe, or North America.

| General Information        |               |                   |              |
|----------------------------|---------------|-------------------|--------------|
| Appearance                 | Colorless     |                   |              |
| Forms                      | Film          |                   |              |
| Physical                   | Nominal Value | Unit              | Test Method  |
| Density                    | 1.06          | g/cm <sup>3</sup> | DIN 53479    |
| Films                      | Nominal Value | Unit              | Test Method  |
| Tensile Strength           | > 14.0        | MPa               | ISO 527-3    |
| Tensile Elongation (Break) | > 300         | %                 | ISO 527-3    |
| Thermal                    | Nominal Value | Unit              | Test Method  |
| CLTE - Flow                | 4.1E-4        | cm/cm/°C          |              |
| Thermal Conductivity       | 0.14          | W/m/K             | DIN EN 12939 |
| Electrical                 | Nominal Value | Unit              | Test Method  |
| Surface Resistivity        | 2.0E+11       | ohms              | DIN 53482    |
| Optical                    | Nominal Value |                   | Test Method  |
| Refractive Index           | 1.478         |                   | DIN 53491    |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT