

SOLLAMID B 2700 FV 15

Polyamide 6
Krisoll Resinas Plásticas Ltda.

Message:
SOLLAMID B 2700 FV 15 is a Polyamide 6 (Nylon 6) material filled with 15% glass fiber. It is available in Latin America. Primary attribute of SOLLAMID B 2700 FV 15: Flame Rated.

General Information				
Filler / Reinforcement		Glass Fiber, 15% Filler by Weight		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.23	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.65 to 0.80	--	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.2	--	%	ASTM D570
Heat Stability	90 to 95	--	°C	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	122	107		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	5500	3300	MPa	ASTM D638
Tensile Strength (23°C)	110	70.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	7.0	%	ASTM D638
Flexural Modulus (23°C)	5200	3300	MPa	ASTM D790
Flexural Strength (23°C)	175	90.0	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	6.0	8.0	kJ/m ²	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	185	--	°C	
1.8 MPa, Unannealed	170	--	°C	
Melting Temperature	214 to 220	--	°C	
CLTE - Flow	3.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	--	ohms · cm	ASTM D257
Dielectric Strength	21	--	kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
NOTE				
1.	Notch B			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

