

Durethan® BKV 240 H2.0 XCP 901510

Polyamide 6

LANXESS GmbH

Message:

PA 6, 40 % glass fibers, injection molding, impact modified, heat-aging stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 40% filler by weight		
Additive		Impact modifier		
		heat stabilizer		
Features		Impact modification		
		Thermal Stability		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.41	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.73	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.13	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.25	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.030	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	11000	6000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	160	100	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	5.5	11	%	ISO 527-2/5
Nominal Tensile Strain at Break (23°C)	--	10	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	10100	6300	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	235	125	MPa	ISO 178/A
23°C ⁶	255	150	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.0	5.5	%	ISO 178/A
ISO Shortname	PA 6-HI,GHR,14-110,GF40	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength				ISO 179/1eA
-30°C	17	--	kJ/m ²	ISO 179/1eA
23°C	28	40	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	110	--	kJ/m ²	ISO 179/1eU
23°C	110	130	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	17	--	kJ/m ²	ISO 180/1A
23°C	28	40	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	95	--	kJ/m ²	ISO 180/1U
23°C	95	110	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	4.70	--	J	ISO 6603-2
23°C	9.10	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	1100	--	N	ISO 6603-2
23°C	1450	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	203	--	°C	ISO 75-2/A
Melting Temperature ⁸	220	--	°C	ISO 11357-3
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	280 - 300		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

