

MAXAMID™ PA6G50HSL-NC010

Polyamide 6
Pier One Polymers, Inc.

Message:
MAXAMID™ PA6G50 is available in natural and custom colors, internal and external lubricants, UV stabilized and other modifications. Further information and details are available upon request.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Additive	heat stabilizer		
	Lubricant		
	UV stabilizer		
Features	UV Stabilized		
	Thermal Stability		
	Lubrication		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.57	g/cm ³	ASTM D792
Ash Content	48 - 52	%	ASTM D4218
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	207	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.5	%	ASTM D638
Flexural Modulus (23°C)	14100	MPa	ASTM D790
Flexural Strength (23°C)	303	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	210	°C	ASTM D648
Peak Melting Temperature	220	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	232 - 288	°C	
Mold Temperature	65 - 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

