

AVALON® 75 AE

Thermoplastic Polyurethane Elastomer (Polyester)

Huntsman Corporation

Message:

AVALON 75 AE is a general purpose polyester based thermoplastic polyurethane for injection moulding.
AVALON 75 AE is part of the AVALON Soft Range and offers a premium soling material for casual, sport and protective footwear.
The features offered include:
Durability
Excellent surface definition
Abrasion resistance
Slip resistance
Phthalate free TPU

General Information			
Features	Good wear resistance		
	Durability		
	General		
	Excellent appearance		
Uses	Sporting goods		
	Footwear		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 2781
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Ross Flex ¹ (-10°C)	2.5E+5	Cycles	
Abrasion Resistance	35.0	mm ³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% strain	4.00	MPa	ISO 37
300% strain	7.00	MPa	ISO 37
Tensile Stress (Break)	24.0	MPa	ISO 37
Tensile Elongation (Break)	600	%	ISO 37
Tear Strength ²	70	kN/m	ISO 34-1
Compression Set (23°C)	20	%	ISO 815
Additional Information			
Test plates conditioned 20 hours at 100°C before testing			
Injection	Nominal Value	Unit	

Drying Temperature - Desiccant Dryer	80.0 - 90.0	°C
Drying Time - Desiccant Dryer	2.0	hr
Hopper Temperature	25.0 - 35.0	°C
Rear Temperature	175 - 185	°C
Middle Temperature	180 - 190	°C
Front Temperature	185 - 195	°C
Nozzle Temperature	175 - 190	°C
Mold Temperature	25.0 - 50.0	°C
Injection Pressure	2.00 - 10.0	MPa
Injection Rate	Slow	
Holding Pressure	1.00 - 5.00	MPa
Back Pressure	0.0300 - 0.300	MPa
Screw Speed	20 - 80	rpm
Screw L/D Ratio	20.0:1.0 to 25.0:1.0	
Screw Compression Ratio	2.0 : 1.0 - 3.0 : 1.0	

Injection instructions

Typical Screw Diameter : 40 - 120 mm3 Stage Design

Feed Zone : 0.4L

Compression Zone : 0.3L

Metering Zone : 0.3L

NOTE

1. BS 5131
2. Method B, right-angle specimen
(without cut)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

