

MACOMASS PP MM-PP HF 24

Polypropylene Homopolymer

MACOMASS Verkaufs AG

Message:

MACOMASS PP MM-PP HF 24 is a Polypropylene Homopolymer (PP Homopolymer) material filled with 30% glass fiber. It is available in Europe.

Important attributes of MACOMASS PP MM-PP HF 24 are:

Chemically Coupled

Homopolymer

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Chemically Coupled		
	Homopolymer		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.09 to 1.13	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.4 to 2.4	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	120	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	> 80.0	MPa	ISO 527-2
Tensile Strain (Break)	> 2.0	%	ISO 527-2
Flexural Modulus	> 4900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	> 8.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	> 30	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	159	°C	ISO 75-2/B
1.8 MPa, Unannealed	138	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

