

Estane® 58202 TPU

Thermoplastic Polyurethane Elastomer (Polyether)

Lubrizol Advanced Materials, Inc.

Message:

Type: Estane® 58202 is an 85A Polyether-Type Thermoplastic Polyurethane (TPU).
Features: Halogenated flame retardant compound with good low temperature properties and cut resistance
Uses: Extrusion - wire and cable jacketing and general extrusion where flame retardant properties are required.

General Information			
UL YellowCard	E106426-218368		
Additive	Flame retardancy		
Features	Halogenated		
	Low temperature resistance		
	Good chemical resistance		
	Oil resistance		
	Good toughness		
	Flame retardancy		
Uses	Cable sheath		
	Wire and cable applications		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Wire & Cable Extrusion		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	82 - 88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles, 1000 g, H-18 Wheel)	155	mg	ASTM D3389
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain, 0.762mm	5.50	MPa	ASTM D412
300% strain, 0.762mm	7.20	MPa	ASTM D412
Tensile Strength (Break, 0.762 mm)	27.6	MPa	ASTM D412
Tensile Elongation (Break, 0.762 mm)	650	%	ASTM D412
Tear Strength			
0.762 mm ¹	62.8	kN/m	ASTM D624

Cracking	19	kN/m	ASTM D470
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-45.0	°C	DSC
Melting Temperature	155	°C	DSC
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Oxygen Index	32	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Drying Temperature	104	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	174	°C	
Cylinder Zone 2 Temp.	179	°C	
Cylinder Zone 3 Temp.	185	°C	
Cylinder Zone 4 Temp.	188	°C	
Adapter Temperature	188	°C	
Melt Temperature	182	°C	
Die Temperature	188	°C	
Extrusion instructions			
Dew Point: -40°C Screen Pack Recommendation: 20/40			
NOTE			

1. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT