

Styrolution PS 576H

High Impact Polystyrene
INEOS Styrolution Group GmbH

Message:

Styrolution PS 576H is a high gloss, high impact polystyrene with a good flow and good heat resistance.

General Information			
UL YellowCard	E108538-100840260		
Features	Good Flow		
	High Gloss		
	High Impact Resistance		
	Medium Heat Resistance		
Uses	Electrical/Electronic Applications		
	Housings		
	Toys		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (200°C/5.0 kg)	5.50	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Water Absorption			ISO 62
Saturation, 23°C	< 0.10	%	
Equilibrium, 23°C, 50% RH	< 0.10	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	83.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2050	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	30.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield, 23°C	1.6	%	
Break, 23°C	30	%	
Flexural Modulus	2100	MPa	ISO 178
Flexural Stress	44.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength			ISO 179

-30°C	70	kJ/m ²	
23°C	120	kJ/m ²	
Notched Izod Impact Strength (23°C)	10	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	88.0	°C	ISO 75-2/B
1.8 MPa, Annealed	78.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	98.0	°C	ISO 306/A50
--	90.0	°C	ISO 306/B50
CLTE - Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+18	ohms·cm	IEC 60093
Electric Strength ¹ (1.50 mm)	160	kV/mm	IEC 60243-1
Dielectric Constant			
100 Hz	2.50		IEC 60250
1 MHz	2.50		IEC 60250
Dissipation Factor (1 MHz)	4.0E-4		IEC 60250
Optical	Nominal Value		Test Method
Gardner Gloss (60°)	70		ASTM D523
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 260	°C	
Mold Temperature	10.0 to 60.0	°C	
Injection Velocity	200	mm/sec	
NOTE			

1. Short Time

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT