

Grilamid® XE 4116 black 9288

Polyamide 1010

EMS-GRIVORY

Message:

Grilamid® XE 4116 black 9288 is a Polyamide 1010 (Nylon 1010) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grilamid® XE 4116 black 9288 are:

- Flame Rated
- RoHS Compliant
- Eco-Friendly/Green
- Good Mold Release

Typical applications include:

- Automotive
- Electrical/Electronic Applications
- Appliances
- Consumer Goods
- Engineering/Industrial Parts

General Information				
Features	Good Flow			
	Good Mold Release			
	Renewable Resource Content			
Uses	Appliance Components			
	Automotive Applications			
	Automotive Exterior Parts			
	Automotive Interior Parts			
	Connectors			
	Consumer Applications			
	Electrical/Electronic Applications			
	Engineering Parts			
	Household Goods			
	Hydraulic Applications			
	Industrial Applications			
	Medical Devices			
	Pneumatic Applications			
RoHS Compliance	Power/Other Tools			
	Sporting Goods			
	RoHS Compliant			
	Black			
Appearance	Granules			
Forms	Injection Molding			
Processing Method				
Physical	Dry	Conditioned	Unit	Test Method

Density	1.59	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.30	--	%	
Flow	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	1.7	--	%	
Equilibrium, 23°C, 50% RH	0.90	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	230	215	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	17500	16500	MPa	ISO 527-2
Tensile Stress (Break)	210	180	MPa	ISO 527-2
Tensile Strain (Break)	2.5	2.5	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	15	14	kJ/m ²	
23°C	20	15	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	85	80	kJ/m ²	
23°C	90	75	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	185	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	150	--	°C	ISO 75-2/C
Continuous Use Temperature				Internal Method
-- ¹	100	--	°C	
-- ²	150	--	°C	
Melting Temperature ³	200	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.0E-5	--	cm/cm/°C	
Transverse	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+12	1.0E+12	ohms·cm	IEC 60093
Electric Strength	36	36	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Flammability Classification (0.800 mm)	HB	--	IEC 60695-11-10, -20
Additional Information	Dry	Conditioned	Test Method
ISO Type	PA1010+X, MH, 16-160, GF 55 --		ISO 1874
NOTE			
1.	Long Term		
2.	Short Term		
3.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT