

SCHULABLEND® (ASA/PA) M/MW NC 100 SF

K2083

Acrylonitrile Styrene Acrylate + Nylon
A. Schulman Europe

Message:
Nanocomposite based on ASA/PA 6-blend with increased dimensional stability, high flow, UV stabilized

General Information			
Processing Method	Injection molding		
Resin ID (ISO 1043)	ASA+PA		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	20.3	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3240	MPa	ISO 527-2/1A/1
Tensile Stress			ISO 527-2/1A/50
Yield	50.5	MPa	ISO 527-2/1A/50
Fracture	48.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	2.8	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	25	%	ISO 527-2/1A/50
Flexural Modulus ¹	3000	MPa	ISO 178
Flexural Stress ²	75.6	MPa	ISO 178
Flexural Strain at Flexural Strength	5.1	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	38	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	106	°C	ISO 75-2/Bf
1.8 MPa, not annealed	70.0	°C	ISO 75-2/Af
Vicat Softening Temperature	120	°C	ISO 306/B50
Additional Information			
1.) Not for use in food contact applications2.) Not for use in medical or pharmaceutical applications			
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

