

EVERCAP™ DMDF-1250 NT 7

High Density Polyethylene Resin

The Dow Chemical Company

Message:

EVERCAP™ DMDF-1250 NT 7 High Density Polyethylene Resin (HDPE) enables the right performance properties to meet demanding closure and fitment application needs. It is intended for use in both compression and injection molded closure applications including carbonated soft drink and hot fill closures. Its unique properties also make it suitable for living hinge closure applications. This resin has been designed to meet demanding performance requirements, especially in the areas of environmental stress crack resistance, impact strength, and sensory, while maintaining good processing characteristics beneficial to molders.

Main Characteristics:

Excellent ESCR, Stiffness, and Impact Strength

Excellent Sensory Properties

Excellent Processing Characteristics

Contains Slip Agent

Complies with:

U.S. FDA 21 CFR 177.1520(c)3.2a

Europe Commission Regulation (EU) No 10/2011

Consult the regulations for complete details.

General Information			
Additive	Sliding agent (1000 ppm)		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.2a		
	Europe No 10/2011		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance			ASTM D1693
50°C, 10% Igepal, F50	272	hr	ASTM D1693
50°C, 100% Igepal, F50	> 2000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	28.3	MPa	ASTM D638
Fracture	22.1	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	9.0	%	ASTM D638
Fracture	690	%	ASTM D638
Flexural Modulus - 2% Secant	1100	MPa	ASTM D790B
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	68.3	°C	ASTM D648

Vicat Softening Temperature	127	°C	ASTM D1525
Melting Temperature (DSC)	130	°C	Internal method
Peak Crystallization Temperature (DSC)	117	°C	Internal method

Additional Information

Plaque molded and tested in accordance with ASTM D 4976.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

